



Description

ECTR-BR is an epoxy and aggregate broadcast anti-slip system, applied at thicknesses between 1.5mm-3mm (1/16ⁱⁿ-1/8ⁱⁿ), and designed to protect new or deteriorated floors. **ECTR-BR** provides excellent resistance against compression, abrasion, impacts and chemicals. **ECTR-BR** meets all kinds of requirements such as durability, performance as well as aesthetics. Seamless plinths are optional with ECTR COVE. This seamless coating from CTM Adhesives offers an unlimited choice of color, and a smooth or non-slip finish can be achieved using very fine to very aggressive aggregates. This system has been approved by the Canadian Food Inspection Agency (CFIA).

This system is composed of:

1. ECTR coloured primer coat 8 mils - 200 ft²/ gal (600 ft² / kit)
2. ECTR coloured 1st broadcast 15mils-106 ft²/ gal (318 ft² /kit)
3. ECTR coloured 2nd broadcast 15mils-106 ft²/ gal (318 ft² /kit)
4. ECTR coloured topcoat 15mils-106 ft²/ gal (318 ft² /kit)

* Broadcast aggregate yield - 1 lbs /ft² (50ft²/bag)

Grade of aggregates available

40 fine

28 medium

16 aggressive

*Optional 2nd top coat of (UCTR-725/UCTR-3500) 10mils – 160 ft²/gal (480ft²/kit)

*Cove base are optional

Primary applications

- ✓ Airplane hangars
- ✓ Pharmaceutical production areas
- ✓ Assembly areas
- ✓ Classrooms
- ✓ Refineries
- ✓ Waste treatment plants
- ✓ Laboratories
- ✓ Areas of light to heavy manufacturing
- ✓ Mechanical rooms
- ✓ Areas of high traffic circulation
- ✓ Etc.

Advantages

- ✓ Contains 100% solids, allowing for interior applications without harmful odors
- ✓ Ideal for reinforcing concrete surfaces
- ✓ Provides a durable anti-slip finish
- ✓ Superior compression strength
- ✓ Impact resistant
- ✓ Impermeable and seamless
- ✓ Seamless coves can be shaped using ECTR-COVE
- ✓ Dense surface resistant to bacteria and moisture and easy to clean

CTM
ADHESIVES



ECTR-BR

Epoxy Broadcast System

-
- ✓ Excellent adhesive properties, allowing for application on a wide variety of substrates
 - ✓ May apply several layers on itself with excellent adhesion
-

CTM Adhesives

CTM Adhesives



TECHNICAL DATA

Packaging liters/ gal us					Color		
11.34 l / 3	15.91 / 4.2	56.71 / 15	Part A	Part B	Mixture		
Recommended Thickness			On Request	Clear - Amber	Like part A		
Optional primer coat ECTR LV / WECT DP	ECTR-LV 8 mils / 200 ft ² us gal WECT-DP 2-4 mils / 400-800 ft ² us gal		Shelf Life				
1 st saturation ECTR	15-20 mils/ 80-106 ft ² us gal		12 months in original unopened factory sealed containers. Keep away from extreme cold, heat, or moisture. Keep out of direct sunlight and away from fire hazards.				
2 nd saturation ECTR	15-20 mils/ 80-106 ft ² us gal						
Top coat ECTR	15-20 mils/ 80-106 ft ² us gal						
Mix Ratio by volume			Consult individual data sheets for the products related to the ECTR-BR system				
A : B = 2 : 1							
<i>*Please note that the indicated mileage is calculated for flat surfaces. A porous or imperfect surface will require more material in order to cover the same mileage.</i>							
Pot life (150g) (ECTR)	VOC (g/litre) (ECTR)	Density (kg/litre) (ECTR)					
50-60 minutes 25°C	106.23	Part A	Part B	Mixture			
Solids by weight %	Recommended Thinner	Clear: 1.11 – 1.13	0.9-1.0	-			
100%	xylene	Colored: 1.11 – 1.15	0.9-1.0	-			
Substrate Temperature		10°C	20°C	30°C			
Waiting Time /Overcoatability (min / max)		16 / 48	8 / 48	5 / 24			
Curing Details	Foot traffic	30 hours	24 hours	16 hours			
	Light traffic	5 days	3 days	2 days			
	Full cure and chemical resistance	10 days	7 days	5 days			
<i>*Note: Times and data mentioned are based on laboratory conditions. Field results may vary and will be affected by changing ambient conditions, especially changes in temperature and relative humidity.</i>							



PROPERTIES @ 23°C (73°F) 50% R.H. (ECTR)

Bond Resistance (psi) ASTM D4541		Permeability (%) ASTM D570			
268(substrate ruptures)		0.3			
Hardness (Shore D) ASTM D2240		Tensile Strength (psi) ASTM D638			
85 - 90		5500			
Compressive Strength ASTM D695		Elongation (%) ASTM D638			
6800		6.7			
Abrasion Resistance, ASTM D4060 (CS17/1000 cycles/ 1000 g)	Viscosity @ 25 °C (cps)	Part A	Part B	Mixture	
	0.10 gram	clear	1200-1400	200 - 400	700-900
		colored	1400-1600	200-400	1000-1200

SURFACE PREPARATION

The surface to be coated must be well primed. Remove dust, laitance, grease, oils, dirt, impregnating agents, waxes, foreign matter, any previous coatings, and disintegrated substances by mechanical means such as shot-blasting (BLASTRAC) or any other approved method to obtain an ICRI-CSP 3-4 profile. The compressive strength of the concrete must be at least 25 MPa (3625 lbs/in²) after 28 days and the tensile strength at least 1.5 MPa (218 lbs/in²).

MIXING

The products must be conditioned at a temperature between 18 ° C (65 ° F) and 30 ° C (86 ° F).

Pre-mixed color (A)

Mix the resin part (A) perfectly before pouring the hardener (part B) according to the indicated mixing ratio. Depending on product amount and size of mixing equipment, mix for 1 to 3 minutes at low speed (300 to 450 rpm). During mixing, scrape the walls and bottom of the container at least once with a trowel to obtain a homogeneous mixture. As the pot life is limited, prepare amount of desired product as required in order to avoid any loss.

Part (A) when adding color pod

Incorporate a full colored container into the clear part (A), and then thoroughly mix until the color is uniform (**one colored container pod per part A gallon**) before pouring in the hardener (part B) according to the indicated mixing ratio. Depending on product amount and size of mixing equipment, mix for 1 to 3 minutes at low speed (300 to 450 rpm). During mixing, scrape the walls and bottom of the container at least once with a trowel to obtain a homogeneous mixture. As the pot life is limited, prepare amount of desired product as required in order to avoid any loss.



APPLICATION

APPLICATION : 1st coat (ECTR) with aggregate broadcast

Apply the coating using a rubber squeegee and pass a roller to obtain a uniform coating. Broadcast the aggregates into the wet coating until full saturation is achieved.

APPLICATION : 2nd coat (ECTR) with aggregate broadcast

Once the first coat has cured completely, remove any excess aggregates and make sure the surface is clean. Apply a 2nd coat of ECTR using a rubber squeegee and pass a roller to obtain a uniform coating. Broadcast the aggregates into the wet coating until full saturation is achieved.

APPLICATION : Top coat (ECTR)

Once the second coat has cured completely, remove any excess aggregates and make sure the surface is clean. Apply a top coat of ECTR using a rubber squeegee and pass a roller to obtain a uniform coating. Repeat this step if a smoother surface is required.

OPTIONAL : Top coat

Replace the ECTR topcoat by an aliphatic or a chemical resistant topcoat, depending on desired application.

CLEANING

Clean all application equipment with the recommended cleaner (SCT-0001). Once the product has hardened, it can only be removed by mechanical means. In case of skin contact, wash thoroughly with warm soapy water.

RESTRICTIONS

- ✓ Do not apply at temperatures below 10 ° C / 50 ° F or above 30 ° C / 86 ° F
- ✓ The relative humidity of the surrounding work environment during the application of the coating and throughout the curing process should not exceed 85%
- ✓ Substrate temperature must be 3 ° C (5.5 ° F) above dew point measured
- ✓ Humidity content of substrate must be <4% when coating is applied
- ✓ Do not apply on porous surfaces where a transfer of humidity may occur during the application
- ✓ The application of this coating on an interior or exterior substrate without a moisture barrier is at risk of detachment (by hydrostatic pressure).
- ✓ Protect the coating from all sources of moisture for a period of 48 hours
- ✓ Surface may discolor in areas exposed to regular ultraviolet light

HEALTH AND SAFETY

In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult with a doctor. For respiratory problems, transport victim to fresh air. Remove contaminated clothes and clean before reuse. Components A and B contain toxic ingredients. Prolonged contact of this product with the skin is susceptible to provoke an irritation. Avoid eye contact. Contact with may cause serious burns. Avoid breathing vapors release from this product. This product is a strong sensitizer. Wear safety glasses and chemical resistant gloves. A breathing apparatus filtering organic vapors approved by the



NIOSH/MSHA is recommended. Predict suitable ventilation. Consult the material safety data sheet for further information.

IMPORTANT NOTICE

The information and recommendations contained in this document are based on reliable test results according to CTM Adhesives Inc. The data mentioned are specific to the material indicated. If used in combination with other materials, the results may be different. It is the responsibility of the user to validate the information therein and to test the product before using it. CTM Adhesives Inc. assumes no legal responsibility for the results obtained in such cases. CTM Adhesives Inc. assumes no legal responsibility for any direct, indirect, consequential, economic or any other damages except to replace the product or to reimbursement the purchase price, as set out in the purchase contract.
